

# BEMADUR® 1K EASY

## 1 – PRODUCT DESCRIPTION

**BEMADUR® 1K EASY** is a one component, solvent free, transparent aliphatic polyurethane binder. It is a moisture curing binder for binding of stones and mineral aggregates to form self draining flooring. **BEMADUR® 1K EASY** formulated to be used indoors or outdoors applications as stone carpet.

## 2– FEATURES

- Excellent adhesion on stone and aggregates
- Solvent free
- UV and color stable
- Easy to apply
- Low odour
- Moisture cure
- Solvent free

## 3 – APPLICATION AREAS

- Binder for quartz and stone carpet floors
- Decorative coatings in external areas, such as terraces and balconies
- Hotel and Shopping Center
- Flooring for courtyards, driveways and pavements
- Warehouses and showrooms

## 4 – APPLICATION PROCEDURE

### Substrate Preparation

It is very important that the surface is prepared correctly to guarantee correct application and the best performance of the product. The most suitable method to prepare the surface is by shot blasting or by grinding with a diamond disk. All dust must then be removed with a vacuum cleaner. Surfaces to be treated with this product must be solid, perfectly clean and dry and have no capillary rising damp (max humidity not higher

than 4%). Remove all traces of dust, grease and form release agents before application. Prime the substrate surface with Mariseal® AQUA PRIMER. Before spreading the mix, make sure the temperature of the substrate is higher than +10°C

### Preparation of the Mix

Mix the **BEMADUR® 1K EASY** with the selected aggregates (natural stone, crushed marble or quartz) with a grain size of 2-4 mm or 4-7 mm at a ratio of binder to aggregates is 4-6% by weight. The ratio between binder and stone is dependent on the absorption of the substrate and the size of stone used. Mix together with a drill at low speed fitted with a spiral mixing attachment or in a normal cement mixer for 10 minutes. The aggregates used in the mix must be dry. Ensure thorough wetting of the filler.

### Application of Mix

The mixture is spread over the substrate with a trowel then is levelled using template strips and finally levelled and compacted with a trowel or a mechanical vibro-compactor (helicopter)

The workability of reactive resins is influenced by the ambient and substrate temperature. At low temperatures the chemical reactions are slowed down; this lengthens the pot life. At the same time the viscosity increases which leads to a higher consumption. High temperature accelerates chemical reactions so that the work time shortened accordingly. Apply the mix at a temperature of between +10°C and +30°C. Clean tools immediately after use with polyurethane thinners. Once hardened, the product may only be removed mechanically.

## 5 – PACKAGING

**BEMADUR® 1K EASY** is packaged in 10 kg cans, 20 kg cans and 205 kg drums.

## 6 – SHELF LIFE & STORAGE CONDITIONS

Shelf life of the unopened original packaging is nine months from manufacturing date. Material should be stored in a tightly closed container. **BEMADUR® 1K EASY** must be protected against moisture. Keep at a temperature between 5°C-30 °C for quality reasons.

## 7 – TECHNICAL FEATURES

	<b>DATAS</b>
<b>Appearance</b>	Clear
<b>Solid content</b>	100 %
<b>Density</b>	1,02 gr/cm <sup>3</sup>
<b>Viscosity</b>	1300-1500 cps
<b>Pot life</b>	240 min
<b>Ready for traffic</b>	48 hr
<b>Complete cure</b>	7 day
<b>Application temperature</b>	+10-30 °C

## 8 – SAFETY

Corrosive and irritating to eyes, skin and lungs. Harmful if swallowed. May be aggravating to asthma, bronchitis, skin allergies and eczema. Wear chemical resistant gloves and eye protection when in contact. Keep container tightly closed when not in use. Please refer SDS for safety information.

## DISCLAIMER

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.